

Net Zero

12x24 Color Body Porcelain



04NETIVO1224



04NETGRA1224



04NETBEI1224



1x3 Mosaic



2x2 Mosaic



04NETLAV1224



04NETARD1224



Tile: 12x24 - 24x24 - 32x32
Mosaic: 1x3 - 2x2
Trim: 3x24 Bullnose - 6x12 Cove Base

For more information
and images:



Net Zero

Color Body Porcelain



Technical Characteristics

Specs	Test Method	Industry Standard	Test Result	
Water Absorption	ASTM C373	$\leq 0.5\%$	$\leq 0.5\%$	
Surface Wear Resistance	ANSI A137.1	Surface wear resistance properties of glazed vitreous and porcelain tile.	All Commercial / Residential	
Chemical Resistance	ASTM C650	No tile sample shows visible defects after continuous contact with a variety of chemicals for 24 hours.	Not Affected	
DCOF (Wet)	ANSI A326.3	<u>Indoor</u> ≥ 0.42	≥ 0.42	
		<u>Outdoor</u> ≥ 0.55	> 0.55	
Stain Resistance	ASTM C1378	Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures.	Not Affected	
Breaking Strength	ASTM C648	≥ 275 lbf	≥ 300 lbf	
Freeze Resistance	ASTM C1026	No tile sample shows visible defects after repeated processes of freezing and thawing.	Resistant	
Warpage Edge	ASTM C485	$\pm 0.40\%$ or ± 0.05 in (± 1.8 mm)	$\pm 0.40\%$	Rectified
		$\pm 0.50\%$ or ± 0.07 in (± 1.8 mm)	$\pm 0.50\%$	Calibrated
Warpage Diagonal	ASTM C485	$\pm 0.40\%$ or ± 0.07 in (± 1.8 mm)	$\pm 0.40\%$	Rectified
		$\pm 0.50\%$ or ± 0.07 in (± 1.8 mm)	$\pm 0.50\%$	Calibrated
Wedging	ASTM C502	$\pm 0.25\%$ or ± 0.03 in (± 0.8 mm)	$\pm 0.25\%$	Rectified
		$\pm 0.50\%$ or ± 0.08 in (± 2.0 mm)	$\pm 0.50\%$	Calibrated
Thickness	ASTM C499	Range: ± 0.04 in	≤ 0.04 in	
Length / Width Variation	ASTM C499	$\pm 0.25\%$ or ± 0.03 in (± 0.8 mm)	$\pm 0.25\%$	

Nominal Size	Actual Size	Thickness	Finish	Rectified
12" x 24"	11.92" x 23.94"	8 mm	Matte	-
24" x 24"	23.94" x 23.94"	8 mm	Matte	-
32" x 32" *	31.5" x 31.5"	8 mm	Matte	Yes
1" x 3" Mosaic	11.7" x 11.7"	8 mm	Matte	-
2" x 2" Mosaic	12" x 12"	8 mm	Matte	-
3" x 24" Bullnose	2.83" x 23.94"	8 mm	Matte	-
6" x 12" Cove Base **	6.5" x 11.8"	7mm	Matte	-

* Sold by full palettes only.

** This item is made to order. Please check with a sales representative for current lead times.

All tile is subject to variations in technical specifications and performance due to the inherent variables in the raw materials and production process. It is understood that test results on a particular product may vary slightly from tile to tile and from test to test. Test results are not guarantees of minimum or maximum thresholds of performance.