
Hero

12x24 Color Body Porcelain











15HERSNO1224

15HERSIL1224


15HERLEA1224

15HERCOA1224









15HERCOR1224

15HERNIG1224

QuickSHIP (noted colors only)

Tile: 12x24

Mosaic: 2x2 (COA, SIL, SNO only)



Tile: 3x12 - 12x24 - 24x48 Mosaics: 2x2 - 12x12 Linear

Trim: 3x24 Bullnose - 6x12 Cove Base















Technical Characteristics

Charactariatio	Test Method	Calibrated		Rectified		Value
Characteristic		Minimum	Maximum	Minimum	Maximum	Value
Nominal Size	ASTM C499	- 3%	+ 3%	- 3%	+ 2%	Compliant
Caliber Range		- 0.5% or - 0.08 in	+ 0.5% or + 0.08 in	- 0.25% or - 0.03 in	+ 0.25% or + 0.03 in	Compliant
Thickness		N/A	Range: 0.4 in	N/A	Range: 0.4 in	Compliant
Wedging	ASTM C502	- 0.5% or - 0.08 in	+ 0.5% or + 0.08 in	- 0.25% or - 0.03 in	+ 0.25% or + 0.03 in	Compliant
Warpage Edge	ASTM C485	- 0.75% or - 0.09 in	+ 0.75% or + 0.09 in	- 0.40% or - 0.05 in	+ 0.40% or + 0.05 in	Compliant
Warpage Diagonal		- 0.5% or - 0.08 in	+ 0.5% or + 0.08 in	- 0.40% or - 0.07 in	+ 0.40% or + 0.07 in	Compliant
		All Porcelain Tiles				
Water Absorption	ASTM C373	≤ 0.5%				≤ 0.5%
Breaking Strength	ASTM C648	Average ≥ 250 lbf; Individual ≥ 225 lbf				≥ 350 lbf avg
Bond Strength	ASTM C482	≥ 50 psi				≥ 100 psi
Resistance to Freeze/ Thaw Cycling	ASTM C1026		Resistant			
Chemical Resistance	ASTM C650		Unaffected			
Stain Resistance	ASTM C1378	As Reported				Unaffected
Dynamic Coefficient of Friction	DCOF (Wet)	Requires a r	> 0.42			
VOC	No VOC					

Nominal Size	Actual Size	Thickness	Finish	Rectified
3" x 12"	2.76" x 11.81"	9 mm	Matte	-
12" x 24"	11.81" x 23.62"	9 mm	Matte	-
24" x 48"	23.62" x 47.24"	9 mm	Matte	Yes
2" x 2" Mosaic	11.75" x 11.75" -OR- 11.81" x 11.81" sheet*	9 mm	Matte	-
12" x 12" Linear Mosaic	11.81" x 11.81"	9 mm	Matte	-
3" x 24" Bullnose	2.83" x 23.62"	9 mm	Matte	-
6" x 12" Cove Base	5.91" x 11.81"	8.5 mm	Matte	-

^{*} Depending on color. See QR code for details.

All tile is subject to variations in technical specifications and performance due to the inherent variables in the raw materials and production process. It is understood that test results on a particular product may vary slightly from tile to tile and from test to test. Test results are not guarantees of minimum or maximum thresholds of performance.



