


78SYMSNO1224



78SYMPER1224



78SYMMOO1224

Decor







Crisp Stacked Mosaic

QuickSHIP (48 Hours)

12x24 - 12x24 Decor Tile: 2x2 - 12x12 Crisp Stacked Mosaic: N/A Trim: Not all colors available in all sizes

For more information and images:



| Technic | al Characteristics | 5 |
|---------|--------------------|---|
| 1 | Test Method | |

| Test Item | Test Method | Test Result |
|---------------------------------|--------------|-----------------------------|
| Water Absorption | ISO 10545-3 | < 0.5% |
| Breaking Strength | ISO 10545-4 | ≥ 43 N/mm² |
| Surface Abrasion Resistance | ISO 10545-7 | PEI 5 |
| Thermal Shock Resistance | ISO 10545-9 | Resistant |
| Frost Resistance | ISO 10545-12 | Resistant |
| Chemical Resistance | ISO 10545-13 | GA (V); GLA (V); GHA (V) |
| Stain Resistance | ISO 10545-14 | Compliant |
| Dynamic Coefficient of Friction | DCOF | > 0.42 |
| Slip Resistance | DIN 51130 | R9 |

| Nominal Size | Actual Size | Thickness | Rectified |
|------------------------|-----------------|-----------|-----------|
| 12" x 24" | 11.81" x 23.62" | 9 mm | Yes |
| 12" x 24" Decor | 11.81" x 23.62" | 9 mm | Yes |
| 2" x 2" Mosaic | 11.81" x 11.81" | 9 mm | - |
| 12" x 12" Crisp Mosaic | 11.81" x 11.81" | 9 mm | - |

Values reflect an average among tests performed in the manufacturer's laboratory according to the standard requirements and/or through a third party laboratory. Tests are performed on actual production, first choice material. Values may vary between single individual production runs.

Installation Note: The TCNA recommends rectangular shape tile be installed with maximum of 33% offset in order to resolve any possible lippage from one tile to the next.





